

Billet Foam Fire Safety

Using a PCI MNL 124 evaluation, our foam core billet panels are rated between two and four hours, depending on size and finish.

Product	Unit Wt.	Rating
8"	54 PSF	2 hours 13 minutes
8.5"	59 PSF	2 hours 33 minutes
12"	73 PSF	4 hours

Using a PCI MNL 124 evaluation, our core fill panels range from three to four hours for 8 inch and 8.5 inch panels.

Product	Core Fills	Rating
8"	2+ cores	3 hours
8"	4 cores	4 hours
8.5"	1 core	3 hours
8.5"	4 core	4 hours

Panel joints are one hour, which can be increased to two, three or four-hour ratings with ceramic felt in the joint.